



Technical Data Sheet

1K-PU Easy Parkettlack

Single-component varnish for
parquet - easy application

Code 4160-XX.PU



DESCRIPTION

It is a ready-to-use single-component polyurethane-based varnish, ideal as a primer-finish treatment for wooden floors, quick and easy. Fast drying, it is characterized by excellent workability and flow even in industrial applications.

To increase the coverage of the coating, it is possible, although not strictly necessary, to apply the Borma Parkettlack 2k primer as a preliminary layer.

Particularly suitable for very absorbent and porous woods.

Available in 10, 30, 60, and 90 gloss versions.

YIELD

80-120 m² /Lt per coat depending on the application method and the degree of absorption of the wood.

FIELDS OF APPLICATION

Interior surfaces in untreated wood. Suitable for the treatment of floors, doors, windows, skirting boards and other wooden objects. Also suitable for wooden furniture.

CLEANING AND DILUTION

Ready to use product. It can be diluted up to 15% with DPU011, Universal Thinner for Polyurethanes.

Characteristics	UM	Value
Density	g/ cm ³	0.88 ± 0.02
Viscosity Ford#4	sec	20 ±1
Dry residue	%	45
Drying time, dust free and overcoating (20°C)	hrs	6-8
Drying time, complete (20° C)	hrs	24

SURFACE PREPARATION



Sand the parquet to obtain a smooth, clean surface free from oils, greases, waxes, silicones and old varnishes. Fill the cracks and surface irregularities. Sanding with 180/220 grit sandpaper leads to a better aesthetic result of the painting. Before applying the first coat, vacuum up all dust residues. The humidity of the wood must be between 9% and 12%.

METHOD OF USAGE



On a previously sanded, clean and degreased support, spread the product evenly with a roller or rag, brush or spray



Leave to dry for 6-8 hours.



Before proceeding with the second coat, sand with 220/240 grit.



Wait 24 hours for complete drying.

TECHNICAL RECOMMENDATIONS

Mix well before use.

Operating temperature not lower than + 10°C. Always ensure adequate ventilation and temperature during and after application to facilitate the drying process. To obtain regular drying, apply uniform and not excessive thicknesses.

It is advisable not to apply in direct sunlight, on hot surfaces, in the presence of strong winds, rain, fog or with the risk of night frosts.

RECOMMENDED CYCLES

To complete the work cycle, the following products are recommended:

1. **Holzmasse Base** cod.0052 binding resin, filled with wood powder.
2. **Holzmasse K2 MDF** cod. 1650XX, two-component putty for wood.
3. **Parkettreiniger** cod. NAT0048 detergent soap for parquet.
4. **Parquet Wax** cod. 0490, self-polishing liquid wax for parquet.

BORMA COLOR SYSTEM



Compatible pastes:
COUP series pigmented pastes

PACKAGING

Code 4160-XX.PU	6 x 500 mL
Code 4161-XX.PU	6 x 1 Lt
Code 4162-XX.PU	2 x 2.5 Lt
Code 4163-XX.PU	2 x 5 Lt
Code 4164-XX.PU	1 x 20 Lt

STORAGE

Store in a cool, well-ventilated place; keep container closed when not in use. Keep away from heat, open flames, sparks and other sources of ignition.

The product has a storage time of 24 months from the production date.

WARNING

Read the SDS before use.

Observe the safety regulations in force.

Product for professional use.

Our technical data sheets are drawn up on the basis of the average results of our tests. However, our technical advice is given in good faith but without warranty. In fact, different substrates, application conditions, systems, dilutions are an integral part of the final result



Interior Line
TRADITIONAL TECHNOLOGY



and often beyond any control. The user must try the products supplied to check if they are suitable for his needs. For our part, we guarantee the continuity of the chemical-physical characteristics.

Product code: **4160-XX.PU**
Revision: **02 of 05.03.2025**