



Technical Characteristic KAI/KOS
FISA TEHNICA

ODU 16.07.05(7/0)

Model Galego bg, Internal code: 9482 , Type Porcelain Tiles GL,
Group Bla, Nominal size 450x450x8.0 mm

Characteristics/Caracteristici Group Bla, Annex G	Tolerance EN 14411:2016, %	Tolerance EN14411:2016, mm	Request values/Valori conform standard	Measured in KAI laboratory/Masuratori in laborator Kai	Testing method/Metoda de lucru
1.Length/width/Lungime/Latime, mm	±0.6/max±2mm	±2.00	450x450mm	1K 447.6x447.6	EN ISO 10545-2
				2K 448.8x448.8	
				3K 450.0x450.0	
				4K 451.2x451.2	
				5K 452.4x452.4	
2.Thickness/Grosimea, mm	±5/max±0.5mm	±0.45	8.0±0.45 mm	8.2 + 8.4mm	EN ISO 10545-2
3. Straightness of sides/Liniaritatea muchiei, mm	±0.5/max±1.5mm	±1.50	±1.30mm	-0.25 + +0.33mm	EN ISO 10545-2
4.Rectangularity/Rectangularitate, mm	±0.5/max±2mm	±2.00	±1.75mm	-0.52 + +0.66mm	EN ISO 10545-2
5. Centre curvature/Curbura centrala, mm	±0.5/max±2mm	±2.00	CC – 1.65 mm; CV + 1.65 mm	-0.09+ +1.17mm	EN ISO 10545-2
6. Edge curvature/Curbura laterală, mm	±0.5/max±2mm	±2.00	CC –1.75mm; CV +1.75mm	-0.30+ +0.73mm	EN ISO 10545-2
7.Warpage/Deformarea, mm	±0.5/max±2mm	±2.00	CC -1.50mm; CV +1.50mm	-0.56+ +0.81mm	EN ISO 10545-2
8. Surface quality/Calitatea suprafetei	≥95% without defects	≥95% without defects	≥98% without defects	Pass	EN ISO 10545-2
9.Water absorption/Absorbția de apa, %	≤0,5% Individual ≤0,6%	≤0,5% Individual ≤0,6%	≤0,5%	0.14%	EN ISO 10545-3
10.Modulus of rupture/rezistența mecanică, thickness≥7.5mm, N/mm²	≥35N/mm² individual≥32N/mm²	≥35N/mm² individual≥32N/mm²	≥35N/mm²	Average: 53.5 N/mm2	EN ISO 10545-4
11. Breaking strength, thickness≥7.5mm, N /Forta de rupere, N	≥ 1300N	≥ 1300N	≥ 1300N	Average: 1 948	EN ISO 10545-4
12.Determination of surface abrasion for glazed tiles/Rezistența la abraziune	the class of abrasive resistance and the number of cycles are declared by producer	the class of abrasive resistance and the number of cycles are declared by producer	Declared value	Class: 3 / 1 500	EN ISO 10545-7
13.Crazing resistance, glazed tiles/Resistența la crapături pentru plăci glazurate	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-11
14. Resistance for household chemicals and swimming pool salts/Rezistența la soluțiile de uz casnic și sărurile de piscină	Min class B	Min class B	Min class B	GA	EN ISO 10545-13
15.Resistance to the low concentration acids and alkalis/Rezistența la acizi și baze de concentrație slabă	Declared value	Declared value	Declared value	GLA	EN ISO 10545-13
16. Resistance to the high concentration acids and alkalis/ Rezistența la acizi și baze de concentrație mare	Declared value	Declared value	Declared value	GHA	EN ISO 10545-13
17.Stain resistance/Rezistența la patare	Declared value	Declared value	Min class 3	class 5	EN ISO 10545-14
18. Frost resistance/Rezistența la îngheț	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Pass according to EN ISO 10545-1	Resistant	EN ISO 10545-12
19.Slipperiness/Rezistența la alunecare	Declared value	Declared value	Declared value	PTV 36 + Dry PTV 25 - 35 Wet	CEN/TS 16165
20. MOHS/Rezistența la zgariere	Declared value	Declared value	Declared value	9	EN 101:1991

Date: 28.05.2024

QC:
/St. Dimitrova/