

S.C. BIALUC SERV CONSULT S.R.L.

E-mail: bialucserv@gmail.com

PELETI RODOS WOOD 15 KG

NR.	PARAMETRI	UNITATE DE MASURA	STANDARD TESTARE	DE	REZULTAT TESTARE
1	DIAMETRU	mm	ISO 17829:2015		$6,19 \pm 0,03$
2	LUNGIME	mm	ISO 17829:2015		$12,49 < L \leq 34,38$
3	UMIDITATE	W-%	ISO 18134-2:2015		$3,99 \pm 0,06$
4	CONTINUT CENUSA	W-%	ISO 18122:2023		$0,60 \pm 0,05$
5	DURABILITATE MECANICA	W-%	ISO 17831-1:2015		$99,3 \pm 0,1$
6	PUTERE CALORICA	KWH/KG	ISO 18125:2017		$5,035 \pm 0,003$
7	AZOT	W-%	ISO 16948:2015		$0,2060 \pm 0,0004$
8	SULF	W-%	ISO 16994:2016		$0,00221 \pm 0,00002$
9	CLOR	W-%	ISO 16994:2016		$0,00211 \pm 0,00001$
10	TEMPERATURA DE DEFORMARE A CENUSII	°C	EN ISO 21404:2020		1335 ± 5

ATENȚIE!

***Produs care atrage umiditate. A se păstra în locuri uscate!**